



Mobil Aero HF Series

ExxonMobil aviation , Japan

Aviation Hydraulic Fluids

Product Description

Mobil Aero HFA and HF are formulated for aircraft systems where use of hydrocarbon-based hydraulic fluids is required. They are low viscosity products, high VI (viscosity index) fluid with excellent low temperature properties, good anti-wear performance, and good chemical stability. Mobil Aero HFA and HF are composed of mineral base oil stock and contain shear-stable VI improvers.

Features and Benefits

Mobil Aero HF Series aviation hydraulic fluids are designed to meet the demanding requirements of commercial and military aircraft applications. These high quality formulations have a long history of excellent performance and provide long, trouble-free service over a wide range of operating conditions.

Product features and potential benefits include:

Features	Advantages and Potential Benefits
High Viscosity Index (VI)	Allows equipment operation over a wide range of temperatures
Excellent low temperature properties	Provides high performance operation in low ambient conditions
Good chemical and oxidation stability	Resists the formation of acidic constituents, varnishes, and deposits
Meets "super clean" requirements of U.S. Spec. MIL-PRF-5606 (Aero HF)	Ensures reliable performance of pumps, servo-valves and other hydraulic system components

Applications

Mobil Aero HFA is a premium quality fluid that meets the quality requirements of the U.S. Military specification MIL-H-5606A (now obsolete). It has a very high VI and is suitable for use at temperatures down to -54 °C (-65 °F). While this quality fluid is no longer used by the U.S. Military, it is still used in some older, small private, and commercial aircraft. It is also used in industrial and commercial equipment requiring good fluidity at very low temperatures, where Mobil Aero HFA provides long, trouble-free service over a wide range of operating conditions.

Mobil Aero HF is a premium quality fluid that is approved against the most current version of U.S. Military specification MIL-PRF-5606. It has physical properties very similar to Mobil Aero HFA, and also meets "super-clean" requirements required by modern aircraft hydraulic systems. It is intended primarily for military aircraft, but it is also used as a hydraulic fluid for small private and commercial aircraft, and as a strut fluid in landing gear of large commercial aircraft. It is a NATO Code Number H-515 fluid.

Specifications and Approvals

This product is recommended for use in applications requiring:	HF	HFA
Mil-H-5606A		X

This product meets or exceeds the requirements of:	HF	HFA
MIL-PRF-5606J	X	

This product meets or exceeds the requirements of:	HF	HFA
NATO H-515	X	

Properties and Specifications

Property	HF	HFA
API Gravity, °API, ASTM D287	29	30
Acid Number, mgKOH/g, ASTM D664		0.03 (0.2 max)
Barium, mg/kg, ASTM D5185	<1 (10 max)	
Base Oil Specific Gravity 15.6 C/15.6 C, ASTM D287	0.872	
Bulk Modulus, Isothermal secant at 40 C/4000 psi, psi, ASTM D6793	200,000 min	200,000 min
Color, Visual	Red	Red
Copper Strip Corrosion, 72 hrs at 135 C, ASTM D130	1B (2E max)	1B (2E max)
Corrosion and Oxidation Stability, 168 hours at 135 C, Rating, ASTM D4636	PASS	PASS
Density @ 60 F, lb/gal, CALCULATED	7.26	7.26
Evapor. Loss, 6H at 71C, mass %, ASTM D972	12 (20 max)	
Flash Point, Cleveland Open Cup, °C, ASTM D92	107	107 (93 min)
Flash Point, Pensky-Martens Closed Cup, °C, ASTM D93	96 (82 min)	92
Foam, Sequence I, Stability, ml, ASTM D892		0
Foam, Sequence I, Tendency, ml, ASTM D892		36 (65 max)
Four-Ball Wear Test, Scar Diameter, mm, ASTM D4172	0.6 (1.0 max)	
Four-Ball Wear Test, Scar Diameter, 40 kg, 1200 rpm, 1 h, 75 C, mm, ASTM D4172		0.6 (1.0 max)
Kinematic Viscosity -40 F, cSt, ASTM D445		450 (500 max)
Kinematic Viscosity 130 F, cSt, ASTM D445		10.4 (10.0 min)
Kinematic Viscosity @ -40 C, mm ² /s, ASTM D445	450 (600 max)	
Kinematic Viscosity @ -54 C, mm ² /s, ASTM D445	2000 (2500 max)	1900
Kinematic Viscosity @ 100 C, mm ² /s, ASTM D445	5.2 (4.9 min)	5.2
Kinematic Viscosity @ 40 C, mm ² /s, ASTM D445	14.0 (13.2 min)	14.0
Low Temperature Stability, 72 hrs @ - 54 C, FTM 3459		PASS
Low Temperature Stability, 72 hrs @ - 54 C, FTM 791.3458	PASS	
Particulate Contamination, mg/100ml, ASTM D4898	0.2 (0.3 max)	

Property	HF	HFA
Pour Point, °C, ASTM D97	-62 (-60 max)	-64 (-60 max)
Shear Stability, %KV loss, ASTM D2603	15 max	
Specific Gravity 60 F / 60 F, ASTM D1429		0.872
Viscosity Index, ASTM D2270	370	370
Water Content, mg/kg, ASTM D6304	50 (100 max)	
Water, Karl-Fischer, ppm, ASTM D1744		50 (100 max)

Health and Safety

Health and Safety recommendations for this product can be found on the Material Safety Data Sheet (MSDS) @ <http://www.msds.exxonmobil.com/psims/psims.aspx>

All trademarks used herein are trademarks or registered trademarks of Exxon Mobil Corporation or one of its subsidiaries unless indicated otherwise.

06-2020

Exxon Mobil Corporation

3225 Gallows Road

Fairfax, VA 22037-0001

1800 662-4525

<http://www.exxonmobil.com>

Due to continual product research and development, the information contained herein is subject to change without notification. Typical Properties may vary slightly.

Energy lives here™

ExxonMobil

Exxon Mobil  

-
-

© Copyright 2003-2019 Exxon
Mobil Corporation. All Rights
Reserved